

RUST-OLEUM®
INDUSTRIAL



FILLCOAT® WATERPROOFING

Stops leaks instantly

- Thick elastic waterproof coating
- Excellent adhesion to various substrates
- Can be applied in all weather conditions
- Renovation of weathered roofs
- Can be applied by brush, roller or airless

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

FILLCOAT® WATERPROOFING

DESCRIPTION

Instantly waterproof elastic paint for roofs, non-walkable terraces, gutters, ridge-pieces, chimney stacks, pipes, etc.

RECOMMENDED USE

Waterproof finish of roofs, non-walkable terraces, gutters, ridge-pieces, chimney stacks, pipes etc. Recoatable with Dacfill, Coating PRT or Dacfill HZ.

TECHNICAL DATA

Density (g/cm ³):	1,05
Gloss Level:	Satin
Solids Content in weight:	52%
Solids content in volume:	43%

DRY TIMES BY 20° C/RV 50%

Touch dry:	4 h
Dry to recoat:	3 - 14 days with the same product. 6 weeks with a paint

RECOMMENDED WET FILM THICKNESS

1000 µm

RECOMMENDED DRY FILM THICKNESS

430 µm

THEORETICAL CONSUMPTION

1 coat of 1 - 1,5 l/m².

Apply 2 coats in combination with the Dacfill-fleece (see below).

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Remove dust, mud, grease, moss and withered leaves carefully. The spots to be repaired are cleaned with a hard broom and sponged. After cleaning, Fillcoat can be applied directly on bituminous substrates, hard PVC, polyester, zinc, aluminium, glass, tiles, etc. Porous materials (concrete, stone, wood) must first be dried and pre-treated with a coat of Primer 44HS. In case of repeatedly repaired spots, important or active cracks, Fillcoat without fibres is to be reinforced with Dacfill-fleece: apply a coat of Fillcoat (about 1 l/m²), unroll Dacfill-fleece in it and cover it immediately with another coat of Fillcoat.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Can be applied during all weather conditions, except for snow.

APPLICATION & THINNING: BRUSH

Do not dilute.

APPLICATION & THINNING: ROLLER

Do not dilute.

APPLICATION & THINNING: AIRLESS SPRAY

Do not dilute. Nozzle: 18 - 23 / Pressure: 220 bars.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Not recommended

CLEANING OF EQUIPMENT / SPILLS

Thinner 22 or white spirit.

REMARKS

Never apply to polystyrene insulation or onto new concrete (concrete should be at least 2 years old). Do not apply Fillcoat as priming coat under Dac Hydro Alu.

SAFETY DATA

VOC level:	485 g/l
VOC ready mix:	485 g/l
VOC category:	A/1
VOC limit:	500 g/l
Grenelle:	Exterior
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 18/08/2021

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu